

Qplast™

QPH 12NA

Homopolymer Polypropylene

Qplast™ QPH 12NA is specifically designed for injection molding applications, featuring an anti-static agent and nucleation, and is produced using non-phthalate technology.

Supplier



Applications

- Food Containers
- Housewares
- Caps and Closures
- USP, UL listed

Physical

	Typical Value (English)	Typical Value (SI)	Test Method
Density	0.900 g/cm ³	0.900 g/cm ³	ASTM D792
Melt Flow Rate (230°C/2.16 kg)	12 g/10 min	12 g/10 min	ASTM D1238

Mechanical

Tensile Strength at Yield	5500 psi	38 MPa	ASTM D638
Elongation at Yield	7 %	7 %	ASTM D638
Flexural Modulus — 1% Secant	280000 psi	1930 MPa	ASTM D790

Impact

Notched Izod Impact Strength 73°F (23°C)	1.0 ft-lb/in	53 J/m	ASTM D256
---	--------------	--------	-----------

Thermal

DTUL at 66psi — Unannealed	246 °F	119 °C	ASTM D648
----------------------------	--------	--------	-----------

Disclaimer

The information presented in this document is believed to be accurate as of the date of publication. However, it is provided for general informational purposes only. It does not imply any express or implied warranty or quality specification, including but not limited to warranties of merchantability or fitness for a particular purpose. Users are solely responsible for independently assessing whether the product is suitable for their intended use and ensuring that it can be used safely and in compliance with relevant laws and regulations. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document.

