



## Qplast™ QPPLL 2908B Plastomer Polyethylene

Qplast™ QPPLL 2908B is an ethylene 1-hexene plastomer, used in monolayer and multilayer film applications. QPPLL 2908B allows for a lower seal initiation temperature relative to its density, high toughness, stiffness, and reduced coefficient of friction on hot metal surfaces.

Supplier			<b>Oplast</b>		
Applications			<ul> <li>Blown Film</li> <li>Barrier Food Packaging</li> <li>Lamination Film</li> <li>Multilayer Packaging Film</li> </ul>		
Form(s)	Pellets				
Resin Properties					
	Typical Value	(English)	Typical Value	(English)	Test Method
Density	0.908	g/cm³	0.908	g/cm³	ASTM D792
Melt Index (190°C/2.16 kg)	2.0	g/10 min	2.0	g/10 min	ASTM D1238
Peak Melting Temperature	237	°F	114	°C	Proprietary Method
Film Properties					
Tensile Strength at Yield MD	860	psi	5.9	MPa	ASTM D882
Tensile Strength at Yield TD	790	psi	5.4	MPa	ASTM D882
Tensile Strength at Break MD	8600	psi	60	MPa	ASTM D882
Tensile Strength at Break TD	8200	psi	60	MPa	ASTM D882
Tensile Elongation at Break MD	480	%	480	%	ASTM D882
Tensile Elongation at Break TD	570	%	570	%	ASTM D882
Secant Modulus MD — 1% Secant	12950	psi	87	MPa	ASTM D882
Secant Modulus TD — 1% Secant	12950	psi	90	MPa	ASTM D882
Dart Drop Impact	800	g	800	g	ASTM D1709A
Elmendorf Tear Strength MD	210	g	210	g	ASTM D1922
Elmendorf Tear Strength TD	280	g	280	g	ASTM D1922
Optical Properties					
Gloss (45°)	35		35		ASTM D2457
Haze	18.0	%	18.0	%	ASTM D1003

## Disclaimer

The information presented in this document is believed to be accurate as of the date of publication. However, it is provided for general informational purposes only. It does not imply any express or implied warranty or quality specification, including but not limited to warranties of merchantability or fitness for a particular purpose. Users are solely responsible for independently assessing whether the product is suitable for their intended use and ensuring that it can be used safely and in compliance with relevant laws and regulations. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document.

**REV: 2024** 

© 2025 Quantum Polymers, Inc. All rights reserved. 1900 Spring Rd suite 430, Oak Brook, IL 60523

quantumpolymers.com